



# Fabric Specification Sheet

## Preliminary

<b>Style:</b>	<b><u>Apagòn Style III</u></b>
<b>Construction:</b>	3 ply (62.1% vinyl, 31.6% fiberglass, 6.2% Proprietary Coating) (Each vinyl is equal thickness and weight)
<b>Surface Texture:</b>	Back side Laminated with Coated front side
<b>Colors Available:</b>	Refer to Product Index
<b>Thread Count:</b>	59 threads per square inch (23 per square centimeter)
<b>Available Widths:</b>	98" (249 cm) Other widths Available upon request
<b>Roll Lengths:</b>	30-yard standard (27 Meters)
<b>Shipping:</b>	Rolls shipped on 3" (7.62 cm) ID paper
<b>Weight Per Sq. Yard:</b>	12.8 ounces (+ or - 2.0) (436.7 grams/m <sup>2</sup> ) (+ or - 68)
<b>Thickness:</b>	13.1 mil (+ or - 2.0) (.333 millimeters) (+ or - .05)
<b>Tear Strength:</b>	Warp 17.13 Lbs/In      Fill 11.43 Lbs/In
<b>Breaking Strength:</b>	Warp 298.26 Lbs/In      Fill 299.72 Lbs/In
<b>Washability:</b>	Material may be dusted with a damp cloth. When scrubbing is necessary, warm water, mild detergents, and gentle rubbing are recommended.
<b>Opacity: Visual check</b>	Blackout
<b>Flammability:</b>	National Fire Protection Association Standard 701 Test Method one 2019 edition
<b>Other Tests Passed:</b>	ASTM D3335 85a Lead Testing Pending- ASTM G21 Testing

MAILING ADDRESS  
P.O. Box 1017  
Warsaw, IN 46581

STREET ADDRESS  
102 Enterprise Drive  
Warsaw, IN 46580

PHONE  
(574) 269-1280

FAX  
(574) 269-7747

E-MAIL  
Mail@indianacoatedfabrics.com

WEBSITE  
www.indianacoatedfabrics.com