

Color #	(2601) Opaque	36"	45"	54"	63"	72"	77"
11	White	X	X	X	X	X	X
23	Bone	X	X	X		X	
34	Clay	X	X	X		X	
26	Buff	X				X	
103	Alabaster	X			X	X	
84	Dark Sand	X				X	
37	Cream	X				X	
32	Champagne	X	X	X		X	
116	Sand Beige	X				X	
38	Ecru	X	X	X		X	
48	Dove Grey	X				X	
47	Grey	X	X	X		X	
49	Dark Grey	X				X	
118	Pewter	X				X	
10	Black	X	X	X		X	
75	Warm White	X				X	
105	Cloud White	X				X	
104	Palomino	X				X	
76	Off White	X				X	
51	Ivory	X	X	X		X	
71	Vanilla	X				X	
57	Oyster	X	X	X	X	X	
134	Suede	X				X	
117	Bark	X				X	
119	Mocha	X				X	
137	Dark Chocolate	X				X	
106	Azure White	X				X	
88	Sky Blue	X				X	
16	Federal Blue	X				X	
19	Navy Blue	X				X	
120	Maroon	X				X	
45	Forest Green	X				X	
121	Bottle	X				X	

OPAQUE

(#11 White Displayed)

Fabric Specification Sheet
the Standard - 12oz 4 Ply Window Shade

Style:	the Standard - 12oz 4 Ply Window Shade		
Construction:	4 ply lamination (73% vinyl and 27% fiberglass) (Each vinyl is equal thickness and weight)		
Surface Texture:	As laminated - Various Embossing Patterns Available		
Thread Count:	60 threads per square inch (23 per square cm)		(+4 / -6)
Available Widths:	36", 45", 54", 63", 72", *77" (91 cm, 114 cm, 137 cm, 160 cm, 183 cm, 196 cm) (Other widths & colors possible, MOQ's may apply) *White & Champagne Only		
Roll Lengths:	30 yards standard (Other lengths available upon request) (27.4 m)		
Weight:	12.5 oz. per square yard (424 grams per square meter)		(+ / - 2.0) (+ / - .68)
Thickness:	12.5 mil (.318 mm)		(+ / - 2.0) (+ / - .05)
Instron Tear Test Lbs./ft.	Warp 26		Fill 18
Instron Breaking Strength Lbs./ft.	Warp 100		Fill 77
Washability:	Material may be dusted with a damp cloth. When scrubbing is necessary, warm water, mild detergents, and gentle rubbing are recommended		
Opacity: Visual check	Blackout		
Flammability:	Meets or exceeds NFPA Standard 701/2010 Edition (Small Scale) Meets or exceeds NFPA 701-89 Large Scale Test Meets or exceeds California State Fire Marshal Section 13115, Registration No. F-35803 Meets or exceeds State of California Administrative Code Title 19 Section 1237.1 (All tests based on 12oz. Opaque/Duplex test)		
Other Tests Passed:	Meets or exceeds ASTM G-21- Resistance to Fungi Meets or exceeds ASTM E1428-9 Meets or exceeds AATCC 16, Option 3- 2003- Colorfastness to Light Meets or exceeds ASTM D4834-03 Lead Test Meets or exceeds CSA-CAN 600.08 Lead Test (All tests based on 12oz. Opaque/Duplex test) UL GreenGuard Gold Certified		

Solar Heat Control Properties
Interior Use at Zero Degree Profile Angle

No.	Color	Ts	Rs	As	Tv	Rv	Av	Tv	O-F	SC (Single Glass)			SC (Insulating Glass)		
										1/8" Cl	1/4" Cl	1/4" H.A	1/2" Cl	1" Cl	1" H.A.
11	White	Tr	77	23	Tr	NA	NA	NA	NA	NA	0.22	NA	NA	0.2	NA
23	Bone	Tr	69	31	Tr	59	41	Tr	0.2	0.27	0.28	0.29	0.26	0.28	0.23
47	Grey	Tr	45	55	Tr	Tr	Tr	NA	NA	0.44	0.43	0.37	NA	NA	NA
49	Dark Grey	Tr	30	70	Tr	28	72	Tr	0.2	0.55	0.53	0.42	0.52	0.49	0.35
10	Black	Tr	5	95	Tr	Tr	Tr	NA	NA	0.72	0.68	0.5	NA	NA	NA

Shipping: Rolls shipped on 3" (7.67cm) ID paper cores
Optional 1.317" (3.2 cm) ID paper cores available

Revised 2/2017

