

SUN ○ PROTECTION

CLASSIC 1150

Number	Colour	Width mm					Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2000	2300	3000	R	T	A	R	T	A			
1078	white	✓	✓	✓	✓	✓	77%	20%	3%	71%	23%	6%	6-7	>0,45	>0,70
1041	off white	✓	✓	✓	✓	✓	74%	21%	5%	70%	22%	8%	6-7	>0,45	>0,70
2398	cream pink	-	-	✓	-	-	63%	17%	20%	61%	18%	21%	6-7	>0,45	>0,70
2397	pearl	-	-	✓	-	-	54%	19%	27%	51%	17%	32%	6-7	>0,45	>0,70
4174	morning mist	-	-	✓	-	-	52%	16%	32%	49%	18%	33%	6-7	>0,45	>0,70
4169	ambrosia	-	-	✓	-	-	59%	18%	23%	57%	17%	26%	6-7	>0,45	>0,70
9202	feather gray	-	-	✓	-	-	42%	14%	44%	40%	12%	48%	6-7	>0,45	>0,70
5208	gletscher	-	-	✓	-	-	49%	16%	35%	48%	15%	37%	6-7	>0,45	>0,70
9165	grey	✓	✓	✓	✓	✓	52%	14%	34%	49%	16%	35%	6-7	>0,45	>0,70
5205	lavender	-	-	✓	-	-	38%	12%	50%	37%	11%	52%	6-7	>0,45	>0,70
1098	antique white	✓	✓	✓	✓	✓	69%	19%	12%	66%	20%	14%	6-7	>0,45	>0,70
2173	wool beige	-	-	✓	-	-	61%	18%	21%	58%	19%	23%	6-7	>0,45	>0,70
2103	beige	✓	✓	✓	✓	✓	64%	19%	17%	60%	17%	23%	6-7	>0,45	>0,70
2309	cream	-	-	✓	-	-	52%	15%	33%	49%	13%	38%	6-7	>0,45	>0,70
6117	french vanille	-	-	✓	-	-	53%	18%	29%	49%	19%	32%	6-7	>0,45	>0,70
9200	silver lining	-	-	✓	-	-	51%	14%	35%	48%	17%	35%	6-7	>0,45	>0,70
9058	anthracite	✓	✓	✓	✓	✓	19%	3%	78%	18%	5%	77%	6-7	>0,45	>0,70
9199	flint grey	✓	✓	✓	-	-	19%	9%	72%	17%	11%	72%	6-7	>0,45	>0,70
9201	smoke grey	-	-	✓	-	-	37%	11%	52%	35%	12%	53%	6-7	>0,45	>0,70
2400	linen	-	-	✓	-	-	26%	16%	58%	24%	18%	58%	6-7	>0,45	>0,70
2326	bleached sand	✓	✓	✓	✓	✓	59%	28%	13%	56%	24%	20%	6-7	>0,45	>0,70
2399	nomad	-	-	✓	-	-	38%	12%	50%	35%	10%	55%	6-7	>0,45	>0,70
6118	cyber yellow	-	-	✓	-	-	47%	18%	35%	42%	19%	39%	6-7	>0,45	>0,70
6119	spectra yellow	-	-	✓	-	-	43%	16%	41%	39%	19%	42%	6-7	>0,45	>0,70
3070	zinnia	-	-	✓	-	-	39%	15%	46%	35%	18%	47%	6-7	>0,45	>0,70
3069	hawaiian sunset	-	-	✓	-	-	26%	11%	63%	24%	13%	63%	6-7	>0,45	>0,70
8167	jester red	-	-	✓	-	-	9%	8%	83%	11%	8%	81%	6-7	>0,45	>0,70
8168	baton rouge	-	-	✓	-	-	11%	10%	79%	14%	12%	74%	6-7	>0,45	>0,70
4170	jasmin green	-	-	✓	-	-	42%	17%	41%	39%	19%	42%	6-7	>0,45	>0,70
4171	fern green	-	-	✓	-	-	26%	13%	61%	24%	15%	61%	6-7	>0,45	>0,70
4172	shadow green	-	-	✓	-	-	39%	15%	46%	37%	17%	46%	6-7	>0,45	>0,70
4173	golden olive	-	-	✓	-	-	24%	14%	62%	22%	15%	63%	6-7	>0,45	>0,70
5207	imperial blue	-	-	✓	-	-	22%	11%	67%	19%	13%	68%	6-7	>0,45	>0,70
5206	hawaiian ocean	-	-	✓	-	-	29%	14%	57%	27%	15%	58%	6-7	>0,45	>0,70
2401	chocolate	-	-	✓	-	-	12%	7%	81%	9%	8%	83%	6-7	>0,45	>0,70
8166	purpur	-	-	✓	-	-	9%	7%	84%	7%	6%	87%	6-7	>0,45	>0,70
5178	marine	-	-	✓	-	-	7%	6%	87%	6%	7%	87%	6-7	>0,45	>0,70
9119	dark grey	✓	✓	✓	✓	✓	9%	8%	83%	8%	9%	83%	6-7	>0,45	>0,70
9198	steel grey	-	-	✓	-	-	8%	5%	87%	7%	7%	86%	6-7	>0,45	>0,70
9092	black	✓	✓	✓	-	-	1%	2%	97%	1%	5%	94%	6-7	>0,45	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Panel Track
 Colour Range 40
 Composition 100 % PES
 Width 89 / 127 / 2000 / 2300 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 190 g/m2
 Thickness 0,30 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.