

SUN PROTECTION

RE-OFFICE 1013


Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	3000	R	T	A	R	T	A			
1000	white	%	%	%	92%	5%	3%	78%	11%	11%	6-7	0,31	0,43
327	grise	%	%	%	85%	4%	11%	78%	6%	16%	6-7	0,31	0,42
9058	anthracite	%	%	%	84%	2%	14%	76%	3%	21%	6-7	0,32	0,42
2025	beige	%	%	%	90%	6%	4%	78%	7%	15%	6-7	0,32	0,43
2378	linen	%	%	%	83%	7%	10%	78%	6%	16%	6-7	0,31	0,44
9164	graphite	%	%	%	83%	1%	16%	74%	3%	23%	6-7	0,32	0,43

Usable for Roller / Vertical / Panel Track
 Colour Range 6
 Composition 100 % PES (recycled)
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 320 g/m²
 Thickness 0,40 mm
 Moisture proofed yes
 PVC free yes
 OekoTex yes



DIN 4102, B1
 BS 5867 part 2
 EN 13773




All printed colours and textures only provide orientation and are not reference pattern.

REVIVAL 1162

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
9196	dust grey	%	%	%	48%	34%	18%	45%	37%	18%	6-7	0,47	0,67
2323	sand	%	%	%	37%	31%	32%	32%	35%	33%	6-7	0,53	0,76
9190	rock	%	%	%	29%	27%	44%	25%	32%	43%	6-7	0,56	0,8
9197	iron	%	%	%	11%	19%	70%	10%	22%	68%	6-7	0,63	0,9

Usable for Roller / Vertical / Panel Track
 Colour Range 4
 Composition 100 % PES (recycled)
 Width 89 / 127 / 2300 mm
 Cutting Process cold
 Processing Direction warp

Weight 150 g/m²
 Thickness 0,35 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.