

SUN PROTECTION

SOLEA 1035

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
325	white	✓	56%	43%	1%	51%	44%	5%	5-6	0,43	0,61
1037	nature white	✓	54%	41%	5%	51%	42%	7%	5-6	0,43	0,61
2453	creme	✓	32%	40%	28%	31%	26%	43%	5-6	0,53	0,76
2459	düne	✓	29%	35%	36%	30%	33%	37%	5-6	0,55	0,79
9279	cement	✓	35%	33%	32%	34%	31%	35%	5-6	0,52	0,74
9280	stone	✓	26%	27%	47%	26%	29%	45%	5-6	0,56	0,80
9290	iron	✓	12%	19%	69%	13%	22%	65%	5-6	0,62	0,89
9291	ash	✓	10%	13%	77%	11%	14%	75%	5-6	0,62	0,89

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Pleated / Panel Track / Vertical on request
 Colour Range 8
 Composition 100 % PES
 Width 2300 mm
 Cutting Process hot
 Processing Direction warp & weft

Weight 220 g/m²
 Thickness 0,45 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes

220 g/m²
 0,45 mm
 yes
 yes
 yes
 yes



suitable for
Workstations



B semi-
transparent



by Gerhard van Clewe
GmbH & Co.KG



Standard 100[®]
by Oeko-Tex[®]

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.