

# SUN PROTECTION

## GALA 1031

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2000	2300	R	T	A	R	T	A			
1017	nature white	✓	✓	76%	15%	9%	72%	19%	9%	6-7	>0,45	>0,75
2413	beach	✓	✓	62%	16%	22%	58%	20%	22%	6-7	>0,45	>0,75
2054	beige	✓	✓	61%	17%	22%	55%	22%	23%	6-7	>0,45	>0,75
9196	dust grey	✓	-	60%	6%	34%	55%	11%	34%	6-7	>0,45	>0,75
9193	silver	✓	✓	64%	15%	21%	61%	19%	20%	6-7	>0,45	>0,75
2412	golden brown	✓	-	53%	16%	31%	49%	21%	30%	6-7	>0,45	>0,75
9030	light grey	✓	✓	67%	14%	19%	63%	19%	18%	6-7	>0,45	>0,75
9190	rock	✓	-	52%	7%	41%	48%	11%	41%	6-7	>0,45	>0,75
2354	copper	✓	-	64%	11%	25%	61%	15%	24%	6-7	>0,45	>0,75
2400	linen	✓	✓	58%	16%	26%	47%	19%	34%	6-7	>0,45	>0,75
9092	black	✓	-	35%	5%	60%	29%	10%	61%	6-7	>0,45	>0,75
2411	dark brown	✓	-	43%	19%	38%	40%	23%	37%	6-7	>0,45	>0,75

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Panel Track  
 Colour Range 12  
 Composition 100 % PES  
 Width 2000 / 2300 mm  
 Cutting Process cold  
 Processing Direction warp & weft

Weight 200 g/m<sup>2</sup>  
 Thickness 0,30 mm  
 Moisture proofed yes  
 PVC free yes  
 Halogen free yes  
 OekoTex yes



Perlex



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.